Mactac IMAGin JT5728P 3.1mil 54" x 164' Matte White Translucent Backlit Print Media

Product Spec Sheet



Call Us at 1-800-944-4573



Version #12 (0217) Approved by J. S.

Product

IMAGin[®] JT5728P

Product Description

JT5728P is a 3.1-mil translucent, **matte** white, soft, polymeric plasticized, calendared PVC film designed for solvent-based ink jet printing. The product is coated on one side with a permanent, clear, acrylic pressure sensitive adhesive and is supplied with an 86# Kraft liner.

JT5728P is designed for internally illuminated signs (light boxes) and window graphics.

Physical Properties

Property	Typical Values	Test Method
Peel Adhesion Ib./in. (N/25mm) 180° on glass - 24 hr.	4.1 - 5.9 (18 - 26)	FTM - 1
Quick Tack, lb./in ² (N/25mm) Glass	4.3 - 6.2 (19 - 27)	FTM - 9
Dimensional Stability, (%) 48 hours @ 158°F	max 0.2	FTM - 14 10" x 10" Sample Bonded to aluminum
Temperature Ranges Minimum Application: End Use:	40°F(+5°C) -40°F to 194°F(-40°C to 90°C)	
Light Transmission (%) Transmission Reflection Absorption	27 66 7	EN410 Varian Carry 5000
Energy properties (%) Transmission Reflection Absorption	32 55 13	EN410


Durability

The outdoor durability of the unprinted film is 5 to 7 years. Overlamination of the inkjet-printed material with IMAGin overlaminates delays eventual color fading that may occur over time. This color fading is mainly dependent upon the inks quality (see technical data sheets given by the ink manufacturers) and the pressure sensitive media being used.

MyBinding.com 5500 NE Moore Court Hillsboro, OR 97124 Toll Free: 1-800-944-4573 Local: 503-640-5920

Shelf Life

2 years from D.O.M. when stored at 60/77°F (15/25°C) and 50% relative humidity in the original package.



To achieve the best possible print quality, please make sure that the correct ICC profiles or printer settings are used. Profiles can be obtained from our Distributors or can be downloaded from www.MyBinding.com . Printer and heater settings and ICC profiles can also be downloaded from some O.E.M. or software manufacturer's websites.

The ICC profiles are provided solely as a customer resource. Print environments, the individual nature of printing systems, inks and software can significantly affect output. It is the customer's responsibility to determine the suitability of any profile for use in their specific print environment.

Glass Breakage

MACtac accepts no liability for glass breakage due to temperature differences across the glass which can be caused by sunlight on dark areas of the graphic. Size, thickness, quality of cut, edge treatment, tinting and frame design all effect temperature stress.

Limitations

- 1) The user is responsible for determining the product's suitability, including adhesion and if needed, removal characteristics when used in applications other than listed specifically in this Performance Guide.
- 2) If there are any questions about applications, please contact your Mactac sales representative to discuss your requirements for recommendations.
- **3)** If this is a printed Performance Guide it is an uncontrolled document. Please check the Mactac website for the latest, most up-to-date version.

Recommendations

Always test your combination of JT5000 products, inks and laminating films prior to commercial use.

- 1) **Printing Conditions:** Print in conditioned pressroom at ±73°F (23°C) and 50% RH. The maximum allowable ink saturation is 270%
- 2) Drying Requirements: Solvent, Eco-solvent and Mild-solvent inkjet prints require 24 48 hr. drying time open to the air. Inks do not dry when printed media is rolled up. <u>The prints must be dry prior</u> to lamination or application.

MyBinding.com 5500 NE Moore Court Hillsboro, OR 97124 Toll Free: 1-800-944-4573 Local: 503-640-5920 3) **Transportation Conditions:** To allow for easy transportation, IMAGin JT5000 series can be rolled up, with the image out, with a minimum diameter of 6 inches (15cm). When the image is not protected by an overlaminate, make sure the print is completely dry and protected in a plastic bag. During transportation or storage, avoid exposing them to extreme temperature and humidity changes.

• Values given are typical and are not necessarily for use in specification.

CALL 1-800-321-8834 for additional product information

IMPORTANT NOTICE: The information given and the recommendations made herein are based on our research and are believed to be accurate, but no guarantee of their accuracy or completeness is made. In every case, user shall determine before using any product in full scale production, or in any way, whether such product is suitable for user's intended use for their particular purpose under their own operating conditions. User assumes all risk and liability whatsoever in connection with their use of any product. The products discussed herein are sold without any warranty as to merchantability or fitness for a particular purpose, or any other warranty, express or implied. No representative of ours has any authority to waive or change the foregoing provisions, and no statement or recommendation not contained herein shall have any force of effect unless in an agreement signed by the officers of seller and manufacturer. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent without authority from the owner of the patent. The following is made in lieu of all warranties, express or implied: Seller's and manufacturer's only obligation shall be to replace or credit such quantity of the product proved to be defective at its discretion.

MyBinding.com 5500 NE Moore Court Hillsboro, OR 97124 Toll Free: 1-800-944-4573 Local: 503-640-5920

