

# Mediashield™ Mattex UV

## Overlaminating Film

Mediashield™ Mattex UV 75µ (3 mil) is a 50µ (2 mil) UV stabilized, clear PVC overlaminating film with a semi-matte finish, coated on one side with a heat activated solvent acrylic adhesive, which is protected by a bleached Kraft grey grid release paper coated on one side with siliconised polyethylene. Available in various sizes.

### Typical Applications

- The soft, non-reflective finish makes it the film of choice for direct graphics.
- When used on inkjet images for trade shows and POS displays, it will cut glare without sacrificing color detail.
- Used to laminate inkjet output printed on canvas.
- As this film is thin and pliable, it conforms well to the canvas weave, maintaining its texture.

### Product Structure

Film	Satin-matte PVC	75µ (3 mil)
Adhesive	Solvent Acrylic (Heat Activated)	
Release Liner	1 Side PE Coated Bleached Kraft Grey Grid Paper (Moisture Stable)	

### Physical Characteristics

Film Thickness	50µ (2 mil)
Adhesive Layer	25µ (1 mil)
Ratio Film/Adhesive	2:1
UV Protection Factor	Film contains UV stabilizers, which prevent film degradation and provide UV protection to the underlying image
Outdoor Durability	3 years
Heat Resistance Range	70°C - 95°C (158°F - 203°F)
Peel Strength (20 min, FTM1)	18 N/25mm

### Process Settings

Equipment Type	Temperature	Speed
Roller Laminator	85°C to 99°C (185°F to 210°F)	0.3m to 1.75m (1 ft to 6 ft) per minute
Press	<b>Not recommended</b>	

### IMPORTANT NOTE:

Information is intended only as a guide and is given without guarantees. Purchasers should independently determine, prior to use, the suitability of each material for their specific purpose. Follow the indications on the package, ask for the safety data sheets and always follow the indications contained therein.

Only the correct use of the product will allow satisfactory results. For this reason, Drytac is not responsible for improper use of the product, either by application or substrate applied to. Make certain that product is right for the desired use, and work according to the instructions given in our technical data sheets. If in doubt of the appropriate application methods or use, contact Drytac at one of the phone numbers listed below.